

YASH BOND SBR



YASH BOND SBR

(Liquid polymer bonding agent for cement containing mixes).

Description

YASH BOND SBR is a one component styrene butadiene rubber latex bonding agent. YASH BOND SBR is designed to improve the physical properties of cement mixes and slurries.

Applications

YASH BOND SBR is ideally designed for use in the following

Applications:

- + Bonding of new to old concrete when used as a slurry coat.
- + To produce polymer modified screeds and floor toppings.
- + To produce a mechanical key prior to rendering of various plaster mixes on concrete, brick and block surfaces.
- + To produce a repair mortar for patching of honeycombed concrete, internally and externally.
- + To produce waterproof renders.

Advantages

- + Successfully increases the bonding/adhesion of cement mixes.
- + Excellent waterproof additive which helps produce waterproof renders, screeds and toppings.
- + Effective plasticizer giving improved workability and cohesion.
- + Improved mechanical and physical properties by increasing tensile, flexural and adhesive strengths.
- + Reduces shrinkage and cracking in repair and screeding mixes.
- + Good freeze/thaw resistance.
- + Chloride free.

Standards

YASH BOND SBR complies with ASTM C1059-99, Type 1 & 2, when tested in accordance with test method ASTM C1042.

Method of Use

Substrate Preparation

The substrate should be sound, clean and free from contamination. Surface laitance should be removed by acid etching.

Technical Properties @ 25°C:

Active solid content	: 48 - 50%
Specific gravity	: Around 1.0
Colour	: White
Ph	: 7 - 10
Slant shear strength ASTM C1042-99	YASH BOND SBR ASTM C1059 Requirements
Type I (dry)	> 8.0 MPa 2.8 MPa
Type II (after immersion)	> 15.0 MPa 8.6 MPa
Shrinkage during cure	: 0.01 - 0.02%

Resistance to water : Excellent

Exposed steel reinforcements should be grit blasted or wired brushed to a bright finish to insure it is clean of all surface contaminants.

For patch repair, cut back the edges of the repair areas to a minimum of 10 mm depth to avoid thin repair thicknesses. Presoak substrates with water prior to commencing the repair.

Mixing

In general, YASH BOND SBR should be added and mixed with the clean water prior to dry materials for better dispersion.

1) As a bonding agent slurry:

The recommended mix to produce slurry consistency can be achieved by mixing 1 YASH BOND SBR : 1 clean water : 3 OPC cement by volume.

2) As a bonding and waterproofing additive for site mixed floor screeds, renders, concrete repair and floor patching: The following table shows the mix designs proposed for the reinstatements of old floors, general purpose patch repair mortar and new floor screeding.

YASH BOND SBR



	<u>Thin Section</u>	<u>Thick Section</u>
	<u>6 - 15 mm</u>	<u>12-40 mm</u>

Cement	50 kg	50 kg
Clean sand	125 kg	75 kg
3 - 6 mm aggregate (preferably granite chips)	-	100 kg
YASH BOND SBR	4 - 7 ltr	4 - 7 ltr
Water	12 - 15 ltr	12 - 15 ltr
Yield approximately	0.10 m ³	0.11 m ³

Application

1) As a bonding agent slurry:

Use a stiff brush to apply a thick coat to presoaked surfaces. Application of the subsequent render, mortar or screed should take place while the bond coat is still wet (tacky). DO NOT apply on dry bond coats. (If bond coat dries before subsequent application, roughen the dry coat before applying a further coat of YASH BOND SBR slurry.)

2) As a bonding and waterproofing additive for site mixed floor screeds, renders, concrete repair and floor patching: Apply the screed, repair mortar or render mix using wooden float to place and compact while the bond coat is still wet (tacky). Finish with a steel float.

Curing

Care should be taken for appropriate curing. Use a chemical curing compound or a wet hessian completely covered with a polyethylene sheet for curing.

Cleaning

All tools should be cleaned immediately after use with fresh clean water. Hardened materials should be cleaned mechanically.

Packaging

YASH BOND SBR is available in 1, 5, 10, 20 and 50 kg containers.

Storage

YASH BOND SBR has a shelf life of 12 months from date of manufacture if stored at temperatures between 5°C and 50°C in closed packaging.

If these conditions are exceeded, YASH Technical Department should be contacted for advice.

Cautions Health and Safety

YASH BOND SBR is nontoxic. Avoid skin and eye contact. Gloves and eye protection should be worn. The use of barrier cream is recommended on exposed areas of the skin. In case of accidental contact with eyes, immediately flush with plenty of water for at least 10 minutes and seek medical advice.

Fire

YASH BOND SBR is non flammable.

More from YASH CONCHEM Products

A wide range of construction chemical products are manufactured by YASH which include:

- Concrete admixtures.
- Surface treatments
- Grouts and anchors.
- Concrete repair.
- Flooring systems.
- Protective coatings.
- Sealants.
- Waterproofing.
- Adhesives.
- Tile adhesives and grouts.
- Building products.
- Structural strengthening.

Note : We endeavor to ensure that any advice, recommendation or information we may give in product literature is accurate and correct. However, due to the fact that we have no direct or continuous control over where or how the products are applied, Yash cannot accept any liability either directly or indirectly arising from the use of Yash products, whether or not in accordance with any advice, specification, recommendation or information given by us.