

YASH SEAL CWP



YASH SEAL CWP

One component acrylic cement modified waterproof coating.

Description

YASH SEAL CWP is a one components; polymer modified cementitious waterproof coating suitable for internal and external applications.

YASH SEAL CWP provides a hardwearing, seamless, waterproof membrane for potable water retaining structures, tanks, basements, foundations and culverts.

Applications

- + Waterproofing for water retaining structures and reservoirs.
- + Waterproofing of basements, roofs, and foundations.
- + Waterproofing of bathrooms and wet areas.
- + Protection of concrete substrates and masonry against carbon dioxide, chloride ions, water and de-icing salts.

Advantages

- + Single component, need only water additions.
- + Non-toxic, approved for use in contact with potable water.
- + Fungus, mould resistant.
- + Excellent bond to porous and non-porous surfaces.
- + Breathable.
- + Durable, excellent protection against carbon dioxide, chloride ions and water.
- + Cost effective, quick and easy brush or spray application.
- + Suitable for internal and external applications.

Method of Use

Substrate Preparation

The surfaces to be coated should be clean, sound, and free from contamination. Remove any traces of curing

compound, laitance, organic growth or any other loose materials. This is best obtained by using high pressure water or light grit blasting. Substrate containing honey combing, damaged or deteriorated concrete should be repaired using suitable repair mortars from YASH repair systems before coating.

Priming

No special primer is required, but substrate should be pre-soaked with clean water prior to application of YASH SEAL CWP.

Technical Properties @ 25°C:

Mixed density	: 1.75 ± 0.05 g/cm ³
Working time	: 1.5 - 2 hr
Color	: Grey powder
Mixing ratio	: 8.5 - 9.5 ltr water / 25 kg bag
Initial setting	: 4 - 5 hr
Application	
Temperature	: 5 - 40°C
Minimum application	
Thickness	: 2 mm (with two coats)

Mixing

To ensure proper mixing, a mechanically powered mixer or drill filled with suitable paddle should be used. Add 8.5 - 9.5 litre of water per 25 kg bag to a clean container. The powder component is then added slowly to the water while mixing continuously with low speed mixer/ drill (400 - 600 rpm). Mixing time should be continued for 3 minutes until a uniform consistency is obtained.

Application

YASH SEAL CWP can be applied by brush, or spray machines. The mixed material should be brushed well into the surface. Strike off with brush in one direction. Care must be taken not to spread the materials too thin. The first coat should be applied at a wet film thickness of 1mm. When the material begins to drag, do not add any water, but dampen the surface again.

YASH SEAL CWP



A minimum of 3 - 5 hours, depending on the prevailing ambient temperature, should be given for the first coat to cure before applying the second coat. If the first coat is fully dried, pre-soaking is needed before applying the second coat.

For brush applications, the second coat should be applied in a perpendicular direction to the previous layer to ensure good bond and coverage.

To achieve a smooth finish, it is recommended to finish the surface with a trowel immediately after brushing the second coat. The total dry film thickness for both coats should be 2 mm.

Remarks

- + YASH SEAL CWP should not be applied to frozen substrates or if ambient temperature is below 5°C or expected to fall below 5°C.
- + The area must not be exposed to moving water during application.
- + YASH SEAL CWP can be submerged with water after 5 - 7 days of application depending on ambient temperatures and relative humidity.
- + Where cementitious plaster is to be applied over YASH SEAL CWP, a mix of sand, cement and YASH BOND SBR should be sprayed over YASH SEAL CWP as key. Addition rate of YASH BOND SBR should be 10 litre/bag of cement.

Cleaning

All tools should be cleaned immediately after finishing using clean water. Hardened materials should be cleaned mechanically.

Packaging

YASH SEAL CWP is available in 25 kg bags.

Coverage

Approximately 19 - 20 m²/25 kg for one coat @ 1 mm thickness.

Storage

YASH SEAL CWP has a shelf life of 9 months from date of manufacture if stored at temperatures range between 5°C and 50°C.

If these conditions are exceeded, YASH Technical Department should be contacted for advise.

Cautions Health and Safety

As YASH SEAL CWP contains Portland cement, YASH SEAL CWP may cause irritation to skin or eyes.

In case of accidental contact with eyes, immediately flush with plenty of water for at least 10 minutes and seek medical advise if necessary.

Fire

YASH SEAL CWP is nonflammable.

More from YASH CONCHEM Products

A wide range of construction chemical products are manufactured by YASH which include:

- Concrete admixtures.
- Surface treatments
- Grouts and anchors.
- Concrete repair.
- Flooring systems.
- Protective coatings.
- Sealants.
- Waterproofing.
- Adhesives.
- Tile adhesives and grouts.
- Building products.
- Structural strengthening.

Note : We endeavor to ensure that any advice, recommendation or information we may give in product literature is accurate and correct. However, due to the fact that we have no direct or continuous control over where or how the products are applied, Yash cannot accept any liability either directly or indirectly arising from the use of Yash products, whether or not in accordance with any advice, specification, recommendation or information given by us.