

YASH EPO GROUT 132



Yash Epo Grout 132

High strength pourable epoxy resin grout

Description

YashEpo Grout 132 is a three component, high strength, free flowing, epoxy resin grout. YashEpo Grout 132 is suitable for grouting gaps with thicknesses between 10 80 mm.

Applications

YashEpo Grout 132 is ideally designed for use in the following applications:

- + Machine base plates.
- + Heavy crane rails.
- + Pile top waterproofing.
- + Bearing plinths.
- + High speed turbines.
- + Grouting areas where occasional chemical spillage may occur.

Advantages

- + Resistant to dynamic loading.
- + Non-shrink and low creep characteristics under continuous loading.
- + Exceptionally high compressive, flexural and tensile strengths.
- + Extremely dense.
- + Exceptional bond to concrete and steel surfaces.
- + Good chemical resistance.
- + High early strength development allowing for rapid installation.

Method of Use

Substrate Preparation

The Substrate should be sound, clean and free from contamination. Surface laitance should be removed by scabbling or grit blasting.

Steel surfaces should be grit blasted to remove all rust and scale.

Concrete surfaces should be dry.

Holes drilled for anchor bolts should be thoroughly cleaned from dust and loose debris using suitable brush or compressed air.

Technical Properties @ 25°C:

Compressive strength:

BS6319, Part 2 : 1983	≥ 90 MPa @ 7 days
Flexural strength: BS6319, Part 3 : 1990	≥ 20 MPa @ 7 days
Fresh wet density:	1.95 ± 0.05
Tensile strength: BS6319, Part 7 : 1985	≥ 9 MPa @ 7 days
Working life:	30 - 40 min @ 25oC 15 - 25 min @ 35oC
VOC:	< 10 g/ltr

Mixing

To ensure proper mixing, a mechanically powered mixer or drill fitted with suitable paddle should be used.

The entire content of the Hardener pack should be added to the Base pack. Care should be taken to ensure that the bottom and the product sides are thoroughly scraped and used. Mix the two components for 2 minutes. The filler should be gradually added while mixing. Mixing should continue for 3 minutes or until a uniform consistency obtained.

Placing and Finishing

Under Base plate:

Enough materials should be available to achieve continuous fill and to complete the work. Pouring of the mixed grout should be started from one side only to avoid air entrapment.

To obtain maximum flow distance, a side shutter feed 100 mm height should be erected and used to build the required head. At 100 mm of head, a flow distance of 1800 mm and 3000 mm can be achieved at gap thicknesses of 40 mm to 75 mm respectively @ 25 °C ambient temperatures.

Formwork:

As the mixed grout possesses high fluid characteristics, all formwork and shutters should be water tight. This can be

YASH EPO GROUT 132



achieved by sealing underneath the formwork and at the joints by using an appropriate mastic.

Notes:

- + If application is Yash under high temperatures, care should be taken because the working time will be reduced significantly.
- + To reduce the effect of this problem, try to store the unmixed materials in a cool environment, avoiding the direct sunlight. Also, try not to make the application in the middle of the day or direct sunlight.

Cleaning

All tools should be cleaned immediately after finishing using a suitable epoxy thinner. Hardened materials should be cleaned mechanically.

Packaging

YashEpo Grout 132 is available in 10 kg/5 litres packs.

Thicknesses and Size Limitations

YashEpo Grout 132 can be applied in a single layer at thicknesses between 10 - 80 mm. For greater thickness, use Flo-Grout EP330.

Yield

Approximately 5 litre/10 kg pack.

Storage

YashEpo Grout 132 has a shelf life of 12 months from date of manufacture if stored at temperatures between 5°C and 35°C.

If these conditions are exceeded, YASH Technical Department should be contacted for advice.

Cautions

Health and Safety

YashEpo Grout 132 is irritant to the eyes, skin and respiratory system. Wear suitable gloves and eye protection. For further information refer to the Material

Safety Data Sheet.

Fire

YashEpo Grout 132 is nonflammable.

More from YASH COCNHEM Products

A wide range of construction chemical products are manufactured by YASH which include:

- Concrete admixtures.
- Surface treatments
- Grouts and anchors.
- Concrete repair.
- Flooring systems.
- Protective coatings.
- Sealants.
- Waterproofing.
- Adhesives.
- Tile adhesives and grouts.
- Building products.
- Structural strengthening.

Note : We endeavor to ensure that any advice, recommendation or information we may give in product literature is accurate and correct. However, due to the fact that we have no direct or continuous control over where or how the products are applied, Yash cannot accept any liability either directly or indirectly arising from the use of Yash products, whether or not in accordance with any advice, specification, recommendation or information given by us.